

Bulletin

Roof Testing Laboratory (ISO/IEC 17025)

UL Third Party Test Data Program participant



Roof System Dynamic Wind Uplift Resistance Results



File number:	DRS-23013266
IKO number:	PARS023-B
Test date:	2023-12-14
Reappraisal date:	2027-04-04

INNOVI TPO 45 MIL OVER IKOTHERM, 16 FASTENERS PER 4' X 8' BOARD

(PARS) PARTIALLY ATTACHED (HYBRID) ROOFING SYSTEM

Tested Roofing System Summary

Cap sheet membrane:	TPO membrane / Adhered
Base sheet membrane:	n/a
Cover board:	Optional
Insulation (top):	Rigid polyisocyanurate foam insulation board 4 x 4 ft x 1½ in / Adhered
Additional insulation (bottom):	Rigid polyisocyanurate foam insulation board 4 x 8 ft x 2½ in / Mechanically fastened
Vapour barrier:	Plastic sheeting / Loose laid
Thermal barrier:	Optional
Decking:	Steel deck

Dynamic Uplift Resistance (DUR) as per CSA A123.21

System Designation	Sustained Pressure (S.P.) (measured)	As per CSA A123.21:20 DUR = (S.P. x 0,65)	As per CSA A123.21:14 DUR = (S.P. ÷ 1,5)
A	-4,6 kPa (-97 psf)	-3,0 kPa (-63 psf)	-3,1 kPa (-65 psf)

According to the scope of accreditation published on the SCC website
File No. 797



Roof Testing Laboratory (ISO/IEC 17025)



Roof System Dynamic Wind Uplift Resistance Results

DRS-23013266

Products

CAP SHEET MEMBRANE				
TESTED PRODUCT: Thermoplastic polyolefin compound laminated on both side of a polyester reinforcement grid.				
System	Securement Method			
A	Fully adhered with InnoviBond Membrane Adhesive LVOC.			
ELIGIBLE PRODUCT(S)				
IKO Industries	Innovi TPO 45 mil	Innovi TPO 60 mil	Innovi TPO 80 mil	

BASE SHEET MEMBRANE				
TESTED PRODUCT: n/a				

COVER BOARD				
TESTED PRODUCT: Optional.				
System	Securement Method			
A	Millennium Adhesive (same rate as insulation)			
ELIGIBLE PRODUCT(S)				
IKO Industries	IKOTherm CoverShield	IKOTherm ShieldPlus		

Roof Testing Laboratory (ISO/IEC 17025)



Roof System Dynamic Wind Uplift Resistance Results

DRS-23013266

INSULATION (top)				
TESTED PRODUCT: Rigid insulation board composed of a closed-cell polyisocyanurate core foamed between two fiber-reinforced organic facers.				
System	Securement Method		Securement Rate	
A	Adhered		Ribbons at 6 in o.c.	
ELIGIBLE THICKNESS(ES)				
1½ in minimum				
SECUREMENT METHOD				
Millennium Adhesive				
SECUREMENT PATTERN				
ELIGIBLE PRODUCT(S)				
IKO Industries	IKOTherm	IKOTherm III	IKOTherm 25 PSI	IKOTherm III 25 PSI
	*IKOTherm Tapered	*IKOTherm III Tapered	*IKOTherm 25 PSI Tapered	*IKOTherm III Tapered 20 PSI

*Always respect board minimum eligible thickness.

Roof Testing Laboratory (ISO/IEC 17025)



Roof System Dynamic Wind Uplift Resistance Results

DRS-23013266

ADDITIONAL INSULATION (bottom and/or additional)				
TESTED PRODUCT: Rigid insulation board composed of a closed-cell polyisocyanurate core foamed between two fiber-reinforced organic facers.				
System	Securement Method		Securement Rate	
A	Mechanically fastened		16 fasteners per 4 x 8 ft board	
ELIGIBLE THICKNESS(ES)				
2½ in minimum				
SECUREMENT METHOD				
Screws and plates				
SECUREMENT PATTERN				
ELIGIBLE PRODUCT(S)				
IKO Industries	IKOTherm	IKOTherm III	IKOTherm 25 PSI	IKOTherm III 25 PSI
	*IKOTherm Tapered	*IKOTherm III Tapered	*IKOTherm 25 PSI Tapered	*IKOTherm III Tapered 20 PSI

*Always respect board minimum eligible thickness.

Roof Testing Laboratory (ISO/IEC 17025)



Roof System Dynamic Wind Uplift Resistance Results

DRS-23013266

VAPOUR BARRIER				
TESTED PRODUCT: Polyethylene plastic sheeting.				
System	Securement Method		Primer	
A	Loose laid		n/a	
ELIGIBLE PRODUCT(S)				
Generic	6 mil polyethylene film	Kraft paper		
IKO Industries	*MVP	*MVP Sand	*Armourbond Flash Sand	ArmourGard-A Vapour Retarder
	ArmourGard Ice and Water Protector Commercial	AcrylicStick SA (primerless)		

* These membranes may be used with an optional primer – see adhesive section for more details.

THERMAL BARRIER				
TESTED PRODUCT: Optional.				
ELIGIBLE PRODUCT(S)				
Georgia-Pacific	DensDeck	DensDeck Prime		
USG	Securock Gypsum Board			
Unifix	PermaBase Dek			
Application method: loose laid, adhered or mechanically fastened. The securement method, rate, and thickness to meet codes requirements, are the designer's responsibilities.				

Roof Testing Laboratory (ISO/IEC 17025)



Roof System Dynamic Wind Uplift Resistance Results

DRS-23013266

FASTENERS (see general note #3)		
TESTED PRODUCT(S)		
System	Screws	Plates
A	InnoviFast Insulation Fastener	InnoviFast Insulation Plate
FASTENERS PULL-OUT RESISTANCE		
1518 N (341 lbf)		
ELIGIBLE PRODUCT(S)		
IKO Industries	InnoviFast Insulation Fastener	InnoviFast Insulation Plate
	InnoviFast All Purpose (AP) Fastener	
	InnoviFast Heavy Duty (HD) Fastener	
SFS	Dekfast DF-#12-PH3	Dekfast PLT-R3 Plate
	Dekfast DF-#14-PH3	
	Dekfast DF-#15-PH3	
Altenloh Brinck & Co US Inc.	Trufast #12 DP	Trufast 3" Metal Insulation Plates
	Trufast #14 DP	
	Trufast #15 DP	

ADHESIVE			
TESTED PRODUCT (for membrane): High strength, solvent based and low volatile organic compounds adhesive (InnoviBond Membrane Adhesive LVOC)			
TESTED PRODUCT (for board stocks): Foamable elastomeric adhesive (Millennium Adhesive).			
System	Application details		Primer (optional for some vapour barriers)
A	Cap sheet: full surface		IKO S.A.M. Adhesive
	Insulation: 6 in o.c.		InnoviBond Membrane Adhesive SPR
ELIGIBLE PRODUCT(S)			
IKO Industries (membranes)	InnoviBond Membrane Adhesive LVOC	InnoviBond Membrane Adhesive	InnoviBond Membrane Adhesive SPR
IKO Industries (insulation)	Millennium Adhesive		

Roof Testing Laboratory (ISO/IEC 17025)



Roof System Dynamic Wind Uplift Resistance Results

DRS-23013266

DECKING				
PRODUCT: Steel deck.				
Grade	Thickness (in)	Yield strength (ksi)	Span spacing (in)	Fasteners spacing (in)
230	0,03	33	54	6
Additional testing could be performed on concrete, plywood, planks, or other substrates to assess eligibility to possible decking equivalencies. On a building, the attachment of the decking to the supporting structure must be strong enough to resist wind uplift loads (as defined per NBC requirements).				

Roof Testing Laboratory (ISO/IEC 17025)



Roof System Dynamic Wind Uplift Resistance Results

DRS-23013266

General Notes

1. Source:

This publication is based on a test conducted by **EXP Services inc.**

2. Deck equivalency products:

Steel deck greater than 22 gage and/or 33 ksi. Wooden deck which testing gives equivalent or superior pull-out resistance than the measured value specified in the "Fasteners Pull Out Resistance" section. For concrete deck, communicate with EXP for possibilities and guidelines.

3. Fasteners Pull Out Resistance:

Tests conducted according to ANSI/SPRI FX-1 standard, over 22 gage, 33 ksi steel deck (unless stated otherwise).

4. Adhesive Pull Resistance (when applicable):

Tests conducted according to ANSI/SPRI IA-1 standard over steel deck (unless stated otherwise) or, according to ASTM D1623 standard.

5. Note on adhesive:

It is EXP opinion that the application of the adhesive beads in an "S" or straight-line arrangement will not affect the results of this publication. The intention at the job site should be that the bead spacings be distributed in reasonably straight lines on the substrate, to come as close as possible to the theoretical patterns when the boards are laid in. Comply with all additional manufacturer's requirements regarding the use of adhesives, among other things, the width of the bead.

6. Liquids, primers, and adhesives:

Observe all application rates specified by the manufacturers, as well as any additional requirements when applying liquids, primers and adhesives.

7. Equivalent products:

Only the products listed in this report under eligible products are deemed acceptable as substitute to the tested products. Any other modifications must be formally requested to EXP to be studied for approval.

8. Optional components:

Any components of this roofing system listed as optional, may be removed from the roof design. Inclusion or exclusion of the said component having no effect on the published dynamic uplift resistance results. (DUR).

9. Building Wind Load Calculation:

An online calculator can compute the Wind Load of any given building, for field, perimeter, and corners, as per 2015 NBC requirement. It will also provide the dimensions of the perimeter and corner areas. The calculator is available at <https://nrc.canada.ca/en/research-development/products-services/software-applications/wind-load-calculators-roof-cladding-vegetated-roof-assembly>

Roof Testing Laboratory (ISO/IEC 17025)



Roof System Dynamic Wind Uplift Resistance Results

DRS-23013266

10. Dynamic Uplift Resistance (DUR) calculation:

CSA A123.21 (2014 and earlier) specified to divide the measured result by 1,5 to obtain the effective wind resistance (DUR).

CSA A123.21 (2020) suggest multiplying the measured result with 0,65 to obtain the effective wind resistance (DUR).

11. Technical Advisories:

This roof system assessment reports must be read in conjunction with any issued technical advisories from EXP.

12. Notice:

EXP reserves the right to withdraw, without prior notice, any Bulletin of Roof System Dynamic Wind Uplift Resistance Results published and/or make any necessary corrections.

The information in this roofing system report (the "Report") are based on the tests run by EXP of certain combination of materials in a specific and controlled condition to determine the resistance of different roofing systems to wind uplift forces (the "Test"). The results of the Test are subject to certain prerequisite conditions and assumptions made during the Test. In this regard, the Report is for the exclusive use of EXP client for whom the Report was prepared. The information contained in the Report must not be reproduced, used, or relied upon, in whole or in part without the written consent of EXP. Any third-party user assumes sole responsibility for the use it makes of the information in the Report including but not limited to any decision to purchase roofing material in reliance of the information found in the Report or on the Site. **Exp disclaims all warranties as to the accuracy, completeness, or adequacy of the information in the Report or on the Site and accepts no responsibility for damages suffered by any third party arising out of decisions made or actions based on the Report.**

13. Version tracking table:

2024-03-18	First edition.
2024-04-04 (R1)	Changes to the name and presentation of eligible products.

Prepared by:

EXP Services Inc.

Serge Rochon, P. Eng.
O.I.Q. N° : 114865
P.E.O. N° : 100023274
Provincial Manager – Building science and CSA laboratory

2024-04-04
Date